



TECHNICAL DATA

102 Barton Street, St. Louis, Missouri 63104

In-State (314) 865-4100/Out of State 800-325-9962/Fax (314) 865-4107 <http://www.schaefferoil.com>

#197 MOLY PURE SYNTHETIC GREASE

Moly Pure Synthetic Grease is a multi-purpose, extreme pressure, wide temperature range grease that is specially formulated for use in all types of heavy duty equipment that is being used under the most adverse conditions of excessive pressure, high stock loading, extreme hot or cold temperatures and moisture.

Moly Pure Synthetic Grease is compounded from the highest quality polyalphaolefin (PAO) synthetic base oils available. Blended into these polyalphaolefin base oils is a bentone base thickener and selected additives. This formulation provides Moly Pure Synthetic Grease with the following outstanding performance features:

1. A wide temperature application range of -50°F to $+500^{\circ}\text{F}$.
2. Extended bearing life, even at elevated temperatures and speeds.
3. Excellent low temperature pumpability characteristics at temperatures as low as -50°F .
4. Exceptional rust and oxidation inhibiting characteristics.
5. Excellent resistance to water washout.
6. Excellent anti-wear and extreme pressure load carrying properties.
7. Excellent mechanical and thermal stability.
8. Excellent shear stability.

Further blended into this blend of polyalphaolefin base oils, bentone thickener and selected additives is molybdenum disulfide. The molybdenum disulfide gives Moly Pure Synthetic Grease the ability to act as a "backstop" lubricant when the grease base's fluid film lubrication. This "backstop" is created by the molybdenum disulfide's natural affinity for metal surfaces. The molybdenum disulfide plates to the metal surface to form a long lasting solid lubricant film. This solid lubricant film will withstand pressures up to 500, 000 pounds per square inch, giving the metal surfaces of the bearing the protection they need during periods of high speed, high shock loads and extreme pressure.

The Moly's solid lubricant film also helps to reduce friction. This reduction in friction results in reduces wear and a reduction in contact area temperature. This results in increased working life of the grease, equipment life, less downtime and extended lubrication cycles.

Moly Pure Synthetic Grease is compatible with all types of seal materials. However, Moly Pure Synthetic Grease is not compatible with soap base greases such as aluminum complex, lithium 12-hydroxystearate, lithium, lithium complex, calcium, calcium complex soap base greases and polyurea base greases.

Typical Properties on Next Page

TD-197 (Rev. 10/2013)

TYPICAL PROPERTIES

NLGI Grade	2
Worked Penetration 77°F/25°C (ASTM D-217)	265 to 295
Type Thickener	Bentone
Dropping Point °F/°C (ASTM D-2265)	None
Rust Inhibition Test (ASTM D-1743)	1,1,1
Oxidation Stability Test (ASTM D-942)	
PSI Loss at 100 hours	2
Timken EP Test (ASTM D-2509)	60
Four Ball EP Test (ASTM D-2596)	
Weld point, kg	315
Load Wear Index, kg	45
Four Ball EP Test (ASTM D-2266)	
Scar Diameter, mm	.68
Falex Continuous Load (ASTM D-3233)	
Failure, lbs.	800
Lincoln Ventmenters	
Psi @ 100°F	200
Psi @ 30°F	575
Psi @ 0°F	700
Psi @ -20°F	850
Psi @ -40°F	1000
Grease Mobility @ 0°F/-18°C US Steel Method	
Flow Rate gram.sec	.34
BASE OIL PROPERTIES:	
Viscosity 40°C cSt (ASTM D-445)	56.5 – 58.5
Viscosity 100°C cSt (ASTM D-445)	8.5 – 9.5
Viscosity Index (ASTM D-2270)	136
Flash Point °F/°C (ASTM D-92)	500°/260°
Fire Point °F/°C (ASTM D-92)	540°/282.°
Pour Point °F/°C (ASTM D-97)	-40°/-40°