

## 221 MOLY ULTRA

Moly Ultra is a versatile, multi-purpose extreme pressure aluminum complex base grease that is specially formulated for use in all types of heavy-duty automotive, construction, mining, farming and industrial equipment and electric motor applications that are being used under the most adverse conditions of excessive pressure, high shock loading, extreme hot and cold temperatures, and moisture.

Moly Ultra is compounded from the finest select high viscosity index solvent refined severely hydro-finished 100% pure paraffin base oils available. Blended into these 100% pure paraffin base oils are an aluminum complex base thickener and selected additives. This formulation provides Moly Ultra with the following outstanding performance features.

- Excellent pumpability characteristics for use in centralized lube systems.
- Excellent resistance to water washout and water spray off.
- Excellent shear and mechanical stability.
- Excellent anti-wear and extreme pressure load carrying properties.
- 100% reversibility. This property allows Moly Ultra to have the ability to retain its grease-like consistency and remain in the bearings during periods of heat, high shock loading, extreme pressure, and severe mechanical action.
- Excellent rust and oxidation inhibiting characteristics.
- Excellent resistance to oxidation.
- A high dropping point.

Incorporated into this blend of high viscosity index paraffin base stocks, aluminum complex thickener and selected additives is molybdenum disulfide. The molybdenum disulfide provides Moly Ultra with the ability to act as a "back-stop" lubricant, when the grease base is either destroyed or wiped away due to unexpected loads, start-up or other conditions which exceed the capabilities of the grease base's fluid film lubrication. This "backstop" is created by molybdenum disulfide's natural affinity for metal surfaces. The molybdenum disulfide plates to the metal surface to form a long lasting solid lubricant film. This solid lubricant film will withstand pressures up to 500,000 pounds per square inch, giving the metal surfaces of the bearings the protection they need during periods of high speed, high shock loads and extreme pressure.

This solid lubricant film also helps to reduce friction. This reduction in friction results in reduced wear and a reduction in contact area temperature. This in turn leads to increased bearing life, less downtime and extended lubrication cycles.

Moly Ultra also has excellent adhesive properties. These excellent adhesive properties provide the Moly Ultra with the ability to resist washout, pound out, splatter or squeeze out even under the heaviest load or vibrations.

Moly Ultra can be applied either manually or by a heavy-duty automatic lube system. Moly Ultra #1 has an operating temperature of -10°F to 350°F. Moly Ultra #2 has an operating temperature of 0°F to 350°F.

Moly Ultra meets and exceeds the following specifications and manufacturer's requirements: US Steel 346, 352, 355, 370 371 specifications, Caterpillar MPGM, Caterpillar's 3% Moly Specification, Komatsu, MIL-G-234C, Case-IH 251H, John Deere, New Holland, Ford M1693A, General Motors, Chrysler, P&H 472B, 472C and 472D, Federal Specification VV-G-632A, MIL-G-4343C, MIL-23549C, DODG-24508A(Navy), DODG-85733(AS), JIS K2220, DIN 515825, SKF, Fag, INA, Torrington, Timken, Rexnord Link-Belt Bearing Division, NSK, Koyo, NTN Bearing, and Roller Bearing Company of America.

Continued on next page

## TYPICAL PROPERTIES

<b>NLGI Grade</b>	<b>1</b>	<b>2</b>
Type Thickener	Aluminum Complex	Aluminum Complex
Specific Gravity 60°F	0.885	0.9053
Dropping Point °F/°C (ASTM D2265)	500°/260°	500°/260°
Worked Penetration, 60 stokes 77°F/25°C (ASTM D217)	310-340	280-295
Roll Stability Test (ASTM D1831) % Consistency Change	16	13.8
Rust Inhibition Test (ASTM D1743) Rating	1,1,1	1,1,1
Oxidation Stability (ASTM D942) Psi loss at 100 hr.	2	2
Water Washout Test (ASTM D1264) % Loss 175°F/79°C*	4.2%	4.2%
Water Spray Off (ASTM D4049) % Loss	27	22
Pressure Oil Separation Test, US Steel Method Grams of Oil separation	2	1.8
Timken EP Test (ASTM D2509) Failure Load, lbs.	60	60
Four Ball EP Test (ASTM D2596) Load Wear Index (kg)	41.8	45.1
Weld Point (kg)	315	315
Four Ball Wear Test (ASTM D2266) Scar Diameter	0.6 mm	0.6 mm
Falex Continuous Load (ASTM D3233) Failure, lbs.	1500	1750
Wheel Bearing Leakage Tendency Test (ASTM-1263) Leakage, grams*	1	.6
Deposits*	No deposits	No deposits
Evaporation Loss (ASTM D2595) % Loss 22 hrs. @ 250°F	0.4	0.4
Pressure Oil Separation (ASTM D1742) % Wt. Loss	2	1.5
Lincoln Ventmeter Psi @ 100°F	100	175
Psi @ 30°F	400	525
Psi @ 0°F	1325	1800
Psi @ -10°F	1800	-----
Psi @ -20°F	-----	-----

## BASE OIL PROPERTIES

Viscosity SUS 100°F (ASTM D445)	1300	1300
Viscosity cSt 40°C (ASTM D445)	244.96	244.96
Viscosity cSt 100°C (ASTM D445)	19.71	19.71
Viscosity Index (ASTM D2270)	105	105
Flash Point °F/°C (ASTM D92)	530°/276.7°	530°/276.7°
Fire Point °F/°C (ASTM D92)	570°/298.8°	570°/304.4°